Application No.: Not Yet Assigned

AMENDMENTS TO THE CLAIMS

1. (Original) Reactive dyes as per the hereinbelow indicated and defined general formula (I),

$$\begin{array}{c|c}
D^2 & OH \\
N=N & O \\
MO & O & N \\
MO & O & N \\
MO & O & N
\end{array}$$
(I)

where

D¹ and D² are independently a group of the general formula (1)

$$R^{\frac{1}{2}}$$
 R^{2}

(1)

where

 R^1 and R^2 are independently hydrogen, (C₁-C₄)-alkyl, (C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, cyano, nitro, amido, ureido or halogen; and

X¹ is hydrogen or a group of the formula -SO₂-Z, where

where

Z¹ is hydroxyl or an alkali-detachable group; or

 D^{1} and D^{2} are independently a naphthyl group of the general formula (2)

$$R^3$$
 R^2
 R^2
 R^2
 R^2
 R^2

where

 R^3 and R^4 are independently hydrogen, (C₁-C₄)-alkyl, (C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, cyano, nitro, amido, ureido or halogen; and

 X^2 has one of the meanings of X^1 ; or

D¹ and D² are independently a group of the general formula (3)

$$R^7 - N$$
 R^6
 R^5
 SO_3M

(3)

where

 R^5 and R^6 independently have one of the meanings of R^1 and R^2 ;

R⁷ is hydrogen, (C_1-C_4) -alkyl, unsubstituted or (C_1-C_4) -alkyl-, (C_1-C_4) -alkoxy-,

sulfo-, halogen- or carboxyl-substituted phenyl; and is a heterocyclic reactive radical; or

 D^{1} and D^{2} are independently a group of the general formula (9)

$$R^{12}$$
 N
 R^{13}
 R^{14}
 X^{3}
 R^{14}

 z^2

where

 R^{12} is hydrogen, (C_1-C_4) -alkyl, aryl or a substituted aryl radical;

 R^{13} and R^{14} are independently hydrogen, (C₁-C₄)-alkyl, (C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, cyano, nitro, amido, ureido or halogen; and

A is a phenylene group of the general formula (10)

where

 R^{15} and R^{16} are independently hydrogen, (C₁-C₄)-alkyl,

(C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, cyano, nitro, amido, ureido or halogen; or

a naphthylene group of the general formula (11)

where

R¹⁷ and R¹⁸ are independently hydrogen, (C₁-C₄)-alkyl,

(C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, cyano, nitro, amido, ureido or halogen; or

a polymethylene group of the general formula (12)

$$-(CR^{19}R^{20})_{k}$$
 (12)

where

k is a whole number greater than 1 and R^{19} and R^{20} are independently hydrogen, (C₁-C₄)-alkyl,

 $(C_1\text{-}C_4)\text{-}alkoxy$, hydroxyl, cyano, amido, halogen or aryl; and

X has one of the meanings of X ; and

 R, R^* are independently hydrogen, (C_1 - C_4)-alkyl or sulfomethyl; and

M is hydrogen, an alkali metal or one equivalent of an alkaline earth metal, with the proviso that the dyes of the general formulae (I) contain at least one fiber-reactive heterocyclic group of the general formula.

2. (Currently amended) Reactive dyes as per claim 1, wherein Z² is a group of the general formula (4) or (5) or (6)

where

V is fluorine or chlorine;

U¹, U² are independently fluorine, chlorine or hydrogen; and

Q¹, Q² are independently chlorine, fluorine, cyanamido, hydroxyl,

(C₁-C₆)-alkoxy, phenoxy, sulfophenoxy, mercapto,

(C₁-C₆)-alkylmercapto, pyridino, carboxypyridino, carbamoylpyridino or a group of the general formula (7) or (8)

$$-N$$
 $N = -N$
 $N = -$

where

 R^8 is hydrogen or (C_1-C_6) -alkyl, sulfo- (C_1-C_6) -alkyl or phenyl unsubstituted or substituted by (C_1-C_4) -alkyl, (C_1-C_4) -alkoxy, sulfo, halogen, carboxyl, acetamido, ureido;

 R^9 and R^{10} independently have one of the meanings of R^8 or combine to form a cyclic ring system of the formula - $(CH_2)_j$ -, where j is 4 or 5, or alternatively - $(CH_2)_2$ -E- $(CH_2)_2$ -, where E is oxygen, sulfur, sulfo, - NR^{11} where $R^{11} = (C_1-C_6)$ -alkyl;

- which as wherein said 1 or 2 substituted by 1 or 2 substituents, such as wherein said 1 or 2 substitutents are (C₁-C₄)-alkyl, (C₁-C₄)-alkoxy, carboxyl, sulfo, chlorine, bromine, or is (C₁-C₄)-alkylene-arylene or (C₂-C₆)-alkylene, which can be is optionally interrupted by oxygen, sulfur, sulfo, amino, carbonyl, carboxamido, or is phenylene-CONH-phenylene, which is unsubstituted or substituted by (C₁-C₄)-alkyl, (C₁-C₄)-alkoxy, hydroxyl, sulfo, carboxyl, amido, ureido or halogen, or is naphthylene which is unsubstituted or substituted by 1 or 2 sulfo groups; and
- Z is as defined above.
- 3. (Currently amended) Reactive dyes as <u>per claim 1</u>, <u>per claim 1 and 2</u>, where the substituents R are hydrogen or sulfomethyl and R* is hydrogen.
- 4. (Currently amended) Reactive dyes as per claim 1, at least one of claims 1 to 3, characterized in that the substituents R¹ and R² are hydrogen, methyl, methoxy or sulfo, R³ to R⁶ and R¹² to R²⁰ R¹² to R¹⁶ are hydrogen and R³ to R⁶, R¹⁷ and R¹⁸ are hydrogen or sulfo also sulfo, R⁷ to R¹⁰ are hydrogen or methyl, R⁷ and R⁸ are also phenyl hydrogen methyl or phenyl and R⁹ and R¹⁰ are hydrogen, methyl are also

2-sulfoethyl, 2-, 3- or 4-sulfophenyl, or R^9 and R^{10} combine to form a cyclic ring system which conforms to the formula –(CH₂)₂-O-(CH₂)₂-.

- 5. (Currently amended) Reactive dyes as per claim 1, at least one of claims 1 to 4, characterized in that Z is vinyl, β-chloroethyl or β-sulfatoethyl.
- 6. (Currently amended) Reactive dyes as claimed in <u>claim 2</u>, at least one of claims 1 to 4, characterized in that Q¹ and Q² in the general formula (5) are independently fluorine, chlorine, cyanamido, morpholino, 2-sulfophenylamino, 3-sulfophenylamino, 4-sulfophenylamino, 3-(2-sulfatoethylsulfonyl)phenylamino, 4-(2-sulfatoethylsulfonyl)phenylamino, 3-(vinylsulfonyl)phenylamino, 4-(vinylsulfonyl)phenylamino, N-methyl-N-(2-(2-sulfatoethylsulfonyl)ethyl)amino or N-phenyl-N-(2-(2-sulfatoethylsulfonyl)ethyl)amino.
- 7. (Currently amended) A process for preparing dyes of the general formula (I) as per <u>claim 1</u>, one or more of claims 1 to 6, which comprises <u>diazotizing</u> one equivalent of an amine of the general formula (16)

$$D^{1} - NH_{2}$$
 (16),

where D¹ is as defined in claim 1 being diazotized in conventional manner and the resulting diazonium compound being reacted in a first stage with an aqueous solution or

suspension of one equivalent of a coupling component as per the general formula (17)

where R, R* and M are each as defined in claim 1, to form a monoazo dye as per the general formula (13)

and subsequently one equivalent of an amine of the general formula (18)

$$D^2 - NH_2$$
 (18),

(13)

where D² is as defined in claim 1, being diazotized in conventional manner and the resulting diazonium compound being coupled in the second stage with the monoazo dye of the general formula (13) obtained in the first stage to form the disazo dye of the general formula (I).

Application No.: Not Yet Assigned

Docket No.: 05579-00333-US

8. (Currently amended) The process for preparing dyes of the general formula (I) as per claim 1 one or more of claims 1 to 6 in the event that the groups D¹ and D² as per the general formulae (I) have the same meaning by two equivalents of an amine of the general formula (16) where D¹ is as defined in claim 1 which comprises diazotizing and reacting being diazotized in conventional manner and reacted in a first stage with one equivalent of a coupling component of the general formula (17)

to form a monoazo dye of the general formula (13)

and the second coupling to the disazo dye of the general formula (I) where the groups D^1 and D^2 have the same meaning being carried out subsequently.

9. (Currently amended) An aqueous liquid preparation containing a dye as set forth in <u>claim 1</u> at <u>least one of claims 1 to 8</u> at a level of 5-90% by weight.

Claim 10 cancelled

- 11. (New) Reactive dyes as per claim 2, where the substituents R are hydrogen or sulfomethyl and R* is hydrogen.
- 12. (New) Reactive dyes as per claim 11, characterized in that the substituents R¹ and R² are hydrogen, methyl, methoxy or sulfo, R¹² to R¹⁶ are hydrogen and R³ to R⁶, R¹⁷ and R¹⁸ are hydrogen or sulfo, R⁷ and R⁸ are hydrogen methyl or phenyl and R⁹ and R¹⁰ are hydrogen, methyl 2-sulfoethyl, 2-, 3- or 4-sulfophenyl, or R⁹ and R¹⁰ combine to form a cyclic ring system which conforms to the formula –(CH₂)₂-O-(CH₂)₂-.
- 13. (New) Reactive dyes as per claim 12, characterized in that Z is vinyl, β-chloroethyl or β-sulfatoethyl.
- 14. (New) Reactive dyes as claimed in claim 13, characterized in that Q¹ and Q² in the general formula (5) are independently fluorine, chlorine, cyanamido, morpholino,
 2-sulfophenylamino, 3-sulfophenylamino, 4-sulfophenylamino,

3-(2-sulfatoethylsulfonyl)phenylamino, 4-(2-sulfatoethylsulfonyl)phenylamino, 3-(vinylsulfonyl)phenylamino, 4-(vinylsulfonyl)phenylamino, N-methyl-N-(2-(2-sulfatoethylsulfonyl)ethyl)amino or N-phenyl-N-(2-(2-sulfatoethyl-

sulfonyl)ethyl)amino.

15. (New) A process of dyeing or printing hydroxyl- and/or carboxamido-containing fiber material.which comprises contacting the reactive dyes as per claim 1 with said material.